



# V.V. MINERAL

Keeraikaranthattu, Tisaiyanvillai.

Tamil Nadu. 627657. India.

Ph : +91 4637 271202

Fax : +91 4637 271802

Email : [velmurugan@vymineral.com](mailto:velmurugan@vymineral.com)

## STANDARD GRADE ZIRCON SAND

Version : V 3.0

Revision Date : 01.11.2009

### Typical Chemical Analysis

Elements	Guaranteed	Typical
ZrO <sub>2</sub> + HfO <sub>2</sub>	65 % Min	65.8%
TiO <sub>2</sub>	0.25 % Max	0.17 %
Fe <sub>2</sub> O <sub>3</sub>	0.15% Max	0.07%
U (ppm)	350 Max	306 ppm
Th (ppm)	250 Max	180 ppm
Al <sub>2</sub> O <sub>3</sub>	1.2% Max	0.92%
P <sub>2</sub> O <sub>5</sub>	0.1 % Max	0.06%

### Typical Sieve Analysis

Mesh	MM	Retained % Range
30	0.600	Nil
40	0.425	< 1%
50	0.300	1~5%
60	0.250	4 ~ 7%
70	0.212	10 ~ 20%
80	0.180	10 ~ 20%
100	0.150	25 ~ 40%
120	0.125	25 ~ 35%
140	0.106	2-8%
-140	- 0.106	< 3%

### Typical Mineralogy

Mineral	Typical
Zircon	99.05%
Rutile	0.2%
Sillimanite	0.75%